

Claims

1. A laminated film comprising:

(i) a resin layer (A) containing an acrylic resin, and

5 (ii) a resin layer (B) containing a resin composition, which
composition comprises:

(a) 10 to 98% by weight of a propylene polymer,

(b) 1 to 60% by weight of an inorganic filler, and

(c) 1 to 60% by weight of a thermoplastic elastomer,

10 provided that the sum of the components (a), (b) and (c) is 100%
by weight.

15 2. The laminated film according to Claim 1, wherein the resin
layer (A) contains a transparent layer or a colored layer.

3. The laminated film according to Claim 1, wherein the resin
layer (A) contains at least two layers of a transparent layer
and a colored layer, wherein the transparent layer is an outermost
layer.

20 4. The laminated film according to Claim 1, wherein the
thermoplastic elastomer contains an ethylene- α -olefin
copolymer.

5. The laminated film according to Claim 1, wherein the inorganic filler contains talc.

6. A structure comprising:

5 (I) a laminated film, which comprises:

(i) a resin layer (A) containing an acrylic resin,
and

(ii) a resin layer (B) containing a resin composition,
which composition comprises:

10 (a) 10 to 98% by weight of a propylene polymer,
(b) 1 to 60% by weight of an inorganic filler, and
(c) 1 to 60% by weight of a thermoplastic elastomer,

provided that the sum of the components (a), (b) and (c) is 100%
by weight; and

15 (II) a substrate containing a polyolefin resin,
wherein the substrate is bound to the resin layer (B) of the
laminated film.

7. The structure according to Claim 6, wherein the polyolefin
20 resin contains a propylene polymer.

8. A process for producing a structure, which comprises the steps of:

(1) thermoforming a laminated film comprising:

(i) a resin layer (A) containing an acrylic resin,

and

(ii) a resin layer (B) containing a resin composition, which composition comprises:

- (a) 10 to 98% by weight of a propylene polymer,
- (b) 1 to 60% by weight of an inorganic filler, and
- (c) 1 to 60% by weight of a thermoplastic elastomer,

provided that the sum of the components (a), (b) and (c) is 100% by weight, to obtain a molded laminated film having a form adapted

10 to the form of an injection mold of the following step (2).

(2) fixing the molded laminated film closely on an inner surface of a cavity of the injection mold so as to contact the resin layer (A) of the molded laminated film with the inner surface of the cavity, and

15 (3) injecting a polyolefin resin into the mold to form
a substrate, whereby obtaining a structure wherein the resin
layer (B) side of the laminated film is bound to the substrate.

9. Car exterior or interior parts composed of the structure
20 according to Claim 6.

10. Household electric appliance parts composed of the structure according to Claim 6.